


26GA. LOW GLOSS COLORS - SELECTION GUIDE



REGAL WHITE



SIERRA TAN



SEAL BROWN



SLATE GRAY



COLONIAL RED



EVERGREEN




DARK GRAY



DARK BRONZE



TERRA COTTA



*BURGUNDY



BLACK




ANTIQUE BLACK †

COOLR[®] MAKES A ROOF COOLER

COOLR[®] is a family of sustainable, energy efficient roofing products comprised of 70% Kynar 500[®] or Hylar 5000[®] prepainted metal and acrylic coated Galvalume[®]. COOLR[®] is available in a wide variety of colors, gauges, widths and substrates for low and steep slope applications.

COOLR[®] IS:

- **HIGHLY REFLECTIVE**
Available with emissivity as high as 90% and reflectivity exceeding 25%.
- **EXCEPTIONALLY DURABLE**
Proven to last over 30 years with minimal maintenance and is offered with a non-prorated warranty for most applications. Paint colors retain 95% of their initial reflectance and emittance over time.
- **MADE OF METAL THAT HAS RECYCLED CONTENT AND IS RECYCLABLE**
Environmentally friendly, typically having a minimum recycled content of 25%. 100% recyclable at the end of a long, useful life.
- **AVAILABLE QUICKLY**
Stocked in volume for fast delivery.



*Available at a slight price premium.

† Limited Warranty applies

Colors shown are matched as accurately as possible, but may vary slightly from finished product. Please contact your representative for more information.



**Sheffield Metals
International**

CLEVELAND: 800.283.5262

ATLANTA: 800.929.9359

DALLAS: 877.853.4904

DENVER: 877.375.1477

www.WhyItsCooler.com

CERTIFIED LABORATORY TEST REPORT SUMMARY & STOCK AVAILABILITY MATRIX

COLOR			ISR	EMI.	3 YEAR	SRI	40.375"	48.375"
L/S Regal White	★	L	0.66	0.87	0.66	80	●	●
L/S Sierra Tan	★	L	0.29	0.86	0.30	29	●	●
L/S Seal Brown	★	L	0.30	0.86	0.32	30	●	●
L/S Slate Gray	★	L	0.40	0.85	0.40	43	●	●
L/S Colonial Red	★		0.29	0.85	0.27	28	●	●
L/S Evergreen	★		0.26	0.87	0.26	25	●	●
L/S Dark Gray	★	L	0.32	0.86	0.33	33	●	●
L/S Dark Bronze	★		0.26	0.85	0.25	24	●	●
L/S Terra Cotta	★	L	0.37	0.88	0.36	40	●	●
L/S Burgundy	★		0.25	0.87	0.25	24	●	●
L/S Antique Black	★		0.28	0.85	0.27	27	●	●
L/S Black	★		0.28	0.85	0.27	27	●	●

	ACCELERATED WEATHERING ASTM G 23	SALT SPRAY ASTM B 117	HUMIDITY ASTM D 2247	FORMABILITY ASTM G 522	ADHESION ASTM D 3359	PENCIL HARDNESS ASTM D 3363	SPECULAR GLOSS ASTM D 523	IMPACT RESISTANCE ASTM D 2794	ABRASION RESISTANCE ASTM D 968	TUNNEL TEST ASTM E 84	ACID RESISTANCE ASTM D PROCEDURE 72 (INDEPENDENT OF SUBSTRATE)
Galvalume®	2,000 Hours Chalk: #8 Color: 2AE	2,000 Hours Scribe: 7 1/16" Blisters Field: 10 No Blisters	2,000 Hours Rating: 10 No Blisters	1/8" Mandrel No Cracking No loss of adhesion	No loss of adhesion	HB Minimum	85° = 5-15	3x Metal Thickness in Inch-lb No loss of adhesion	Total Sand = 67 liters Plus or minus 10 liters	Class A Coating	20% Sulfuric Acid 18 hour - No Visible Change

NOTES

- All of Sheffield's **COOLR**® metal is painted with a .20 mil primer and .70 -.90 mil Top Coat of 70% Kynar 500® or Hylar 5000®. The reverse side has a .20 primer and .30 - .40 backer coating.
- For low slope roofing to meet Energy Star requirements the ISR must be ≥0.65. After 3 years, the solar reflectance must be ≥0.50.
- For steep slope roofing to meet Energy Star requirements the ISR must be ≥0.25. After 3 years, the solar reflectance must be ≥0.15.
- For low slope roofing to meet LEED 2009 requirements the SRI must be ≥78.
- For steep slope roofing to meet LEED 2009 requirements the SRI must be ≥29.
- Low slope is defined as ≤2:12.
- Steep slope is defined as >2:12.

KEY

●	Stocked Item
★	Energy Star Compliant
L	LEED Compliant
ISR	Initial Solar Reflectance
EMI	Emissivity
SRI	Solar Reflectance Index

Represented on this chart are our most popular, high quality architectural finishes. We are proud to offer full prime metal and PVDF fluoropolymer coatings. These rich and vibrant colors are produced with either Kynar 500® or Hylar 5000® resins, which provides superior color retention, and allows us to offer non-prorated coating warranties for most applications.

We carry an extensive inventory of painted aluminum and Galvalume® steel as well as acrylic-coated Galvalume®. Custom color matching and specialty paint systems are available upon request. Your sales representative can supply you with additional information on these and our other products.



Sheffield Metals
International



valspar

Oil canning is an aesthetic issue and is an inherent part of light gauge cold formed metal products. By using coil that has been processed properly, designing for thermal movement, following stringent specifications for installation and proper handling most oil canning can be eliminated. Oil canning is not grounds for coil/panel rejection.

Galvalume® is a registered trademark of BIEC International Inc.
Hylar 5000® is a registered trademark of Solvay Solexis, Inc.
Kynar 500® is a registered trademark of Atofina, Inc.